



### Testliner3

#### TİPİK DEĞERLER

TEST	Metot	Birim	TESTLINER3		
Gramaj	T 410	g/m <sup>2</sup>	90	100	115
Rutubet	T 412	%	8,2	8,1	8,0
Patlama	T 403	kPa	149	161	184
Patlama indeksi	T 403	kPa.m <sup>2</sup> /g	1,65	1,61	1,60

#### GARANTİ EDİLEN DEĞERLER

TEST	Metot	Birim	Tolerans	TESTLINER3		
Gramaj	T 410	g/m <sup>2</sup>	% ± 4	90	100	115
Rutubet	T 412	%	± 1,5	8,5	8,5	8,0
Patlama	T 403	kPa	min	126	140	161
Patlama indeksi	T 403	kPa.m <sup>2</sup> /g	min	1,40	1,40	1,40

Test Şartları 23±1°C, 50% ± 2% RH

ISO 9001:2015  
ISO 14001:2015  
ISO 45001:2018  
ISO 50001:2018  
TS 12728



\*Kuru, yağlı olmayan, soyulabilir, yıkanabilir gıdalar ile temasa uygundur.  
İşletme Kayıt No:TR-59-K-016501